

PROPERTIES

	PROPERTIES	VALUE	METOD AND CONDICTION
PHYSICAL & MECHANICAL	Density	1,08 g/cm ³	ISO 1183
	Impact Strength	60 Kj/m ²	ISO 179/2-1eU
	Tensile strength	125 Mpa	ISO 527
	Tensile Modulus	8900 Mpa	ISO 527
	Elongation at break	4,90%	ISO 527
THERMAL	Heat Deflection Temperature	163 °C	ISO 75
	Vicat	171 °C	ISO 306
	Flammability:	HB	