

| Material Properties | METRIC ^{1,2} | IMPERIAL ^{1,2} | METHOD |
|----------------------------------|------------------------------|--------------------------------|---------------------|
| Mechanical Properties | METRIC ^{1,2} | IMPERIAL ^{1,2} | METHOD |
| Ultimate Tensile Strength | 38 MPa | 5510 psi | ASTM D638-14 Type 1 |
| Tensile Modulus | 2800 MPa | 406 ksi | ASTM D638-14 Type 1 |
| Elongation at Break (X/Y) | | 4% | ASTM D638-14 Type 1 |
| Elongation at Break (Z) | | 3% | ASTM D638-14 Type 1 |
| Flexural Properties | METRIC ^{1,2} | IMPERIAL ^{1,2} | METHOD |
| Flexural Strength | 56 MPa | 8122 psi | ASTM D790-15 |
| Flexural Modulus | 2400 MPa | 348 ksi | ASTM D790-15 |
| Impact Properties | METRIC ^{1,2} | IMPERIAL ^{1,2} | METHOD |
| Notched Izod | 36 J/m | 0.67 ft-lb/in | ASTM D256-10 |
| Thermal Properties | METRIC ^{1,2} | IMPERIAL ^{1,2} | METHOD |
| Heat Deflection Temp. @ 1.8 MPa | 113 °C | 235 °F | ASTM D648-16 |
| Heat Deflection Temp. @ 0.45 MPa | 170 °C | 338 °F | ASTM D648-16 |
| Vicat Softening Temperature | 175 °C | 347 °F | ASTM D1525 |
| Other Properties | METRIC ^{1,2} | IMPERIAL ^{1,2} | METHOD |
| Moisture Content (powder) | | 0.23% | ISO 15512 Method D |
| Water Absorption (printed part) | | 0.24% | ASTM D570 |

Samples printed with Nylon 12 GF Powder have been evaluated in accordance with ISO 10993-1:2018, and has passed the requirements for the following biocompatibility risks:

| ISO Standard | Description ^{3,4} |
|---------------------------|----------------------------|
| ISO 10993-5:2009 | Not cytotoxic |
| ISO 10993-10:2010/(R)2014 | Not an irritant |
| ISO 10993-10:2010/(R)2014 | Not a sensitizer |

| Flammability Properties | |
|-------------------------|--------|
| Testing Standard | Rating |
| UL 94 Section 7 | HB * |

* Thickness of the sample tested = 3.00mm

SOLVENT COMPATIBILITY

Percent weight gain over 24 hours for a printed and post-cured 1 x 1 x 1 cm cube immersed in respective solvent:

| Solvent | 24 hr weight gain, % | Solvent | 24 hr weight gain, % |
|---------------------------------|----------------------|--|----------------------|
| Acetic Acid 5% | 0.2 | Mineral oil (Heavy) | 1.0 |
| Acetone | 0.2 | Mineral oil (Light) | 1.3 |
| Bleach ~5% NaOCl | 0.2 | Salt Water (3.5% NaCl) | 0.2 |
| Butyl Acetate | 0.2 | Skydrol 5 | 0.8 |
| Diesel Fuel | 0.6 | Sodium Hydroxide solution (0.025% PH 10) | 0.2 |
| Diethyl glycol Monomethyl Ether | 0.5 | Strong Acid (HCl conc) | 0.8 |
| Hydraulic Oil | 1.0 | Tripolyene glycol monomethyl ether | 0.8 |
| Hydrogen peroxide (3%) | 0.2 | Water | 0.1 |
| Isooctane (aka gasoline) | 0.0 | Xylene | 0.2 |
| Isopropyl Alcohol | 0.2 | | |

¹ Material properties may vary with part geometry, print orientation and temperature.

² Parts were printed using Fuse 1, with Nylon 12 GF powder. Parts were conditioned at 50% relative humidity and 23 °C for 7 days before testing.

³ Material properties may vary based on part design and manufacturing practices. It is the manufacturer's responsibility to validate the suitability of the printed parts for the intended use.

⁴ Nylon 12 GF was tested at NAIMSA World Headquarters, OH, USA.